A Pigment of Your Imagination



TECHNICAL DATA SHEET

Date: 01.09.2024

REACH Status : Registered

Revision : 05

Product Description					
C.I Generic Name	PIGMENT BLUE 15:3		NPPL Product Code	Navfast Blue 9143	
C.I No.	74160		CAS No.	147-14-8	
EINECS No.	205-685-1		Chemical Type	Phthalocyanine Beta Blue	
Molecular Formula	C32H16CuN8		Molecular Weight	576	
Chemical Name: Copper,[29H-phthalocyanineato(2-)-N29,N30,N31,N32]-,(SP-4-1)-					

Physical Properties		
Sieve Residue (PPM) Max.	500	
Oil Absorption (%)	45-55	
Bulk Density (gms/cc)	0.30 -0.45	
Water Soluble Matter (%)	< 1	
Moisture Content (%) Max.	1	
Conductivity µS/CM (max)	500	
PH Value	6.0 – 9.0	

Fastness properties				
Heat °C	Mass Tone	200°C - 280°C / 5 min		
Heat °C	Tint Tone	200°C - 280°C / 5 min		
Light	Mass Tone	8		
Light	Tint Tone	8		
Weather	Mass Tone	5		
Weather	Tint Tone	5		
Migration		5		

Mass Tone : 5%	Tint Tone : 1:9 Ratio

Specification				
Coloristic properties	Strength : ± 5 %			
Coloristic properties	DA,DB,DE,DC,DH,DL: ± 1			
Light fastness : Scale 1-8	1~Poor & 8 ~ Excellent			
Weather fastness : Scale 1-5	1~Poor & 5 ~ Excellent			
Solvent Fastness: Scale 1-5	1~Poor & 5 ~ Excellent			
Heat Stability °C	DE =3 at Maximum Temp.</td			

Application

Application		
Water Based Ink	Suitable	
Textile	Suitable	
Coating	Suitable	
Plastics	Limited Suitability	

Note: The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



CIN No: U24220GJ1998PTC033736

NAVPAD PIGMENTS PVT. LTD.

A Govt. Of India Recognized Star Export House

Regd. Office & Factory: 1196/1/A & B, Ghumasan Patia Road, Chhatral - Mehsana Highway, Rajpur - 382715, Gujarat, India T: +91-982-503-1388 / +91-2764-278338 E: exports@navpadpigments.com W: www.navpadpigments.com

