



Technical Data Sheet

Date: 01.06.2025

Revision : 06


Product Description

C.I Generic Name	Pigment Yellow 17	NPPL Product Code	Navfast Yellow 9029
C.I No.	21105	CAS No.	4531-49-1
EINECS No.	224-867-1	Chemical Type	Diarylide Yellow
Molecular Formula	C34H30CL2N6O6	Molecular Weight	690
Chemical Name: Butanamide,2,2'-[(3,3'-dichloro{1,1'-biphenyl}-4,4'diyl)bis(azo)]bis[N-(2-methoxyphenyl)]-3-oxo			


Physical Properties

Sieve Residue (PPM) Max.	500
Oil Absorption (%)	45-55
Bulk Density (gms/cc)	0.35 -0.50
Water Soluble Matter (%)	<1
Moisture Content (%) Max.	1
Conductivity μ S/CM (max)	500
PH Value	6.5 – 7.5

Mass Tone : 5%



Tint Tone : 1:9 Ratio



Solvent Fastness properties

Water	5
Ethanol	4
Ethyl Acetate	5
MEK	5
Acid	4
Alkali	4

Fastness properties

Heat °C	200°C
Light Mass Tone	6
Light Tint Tone	5
Weather Mass Tone	3
Weather Tint Tone	2-3
Migration	5

Specification

Coloristic properties -Tint	Strength : \pm 5 %
Coloristic properties - Tint	DA,DB,DE,DC,DH,DL: \pm 1
Light fastness : Scale 1- 8	1~Poor & 8 ~ Excellent
Weather fastness : Scale 1- 5	1~Poor & 5 ~ Excellent
Overspray : Scale 1- 5	1~Poor & 5 ~ Excellent
Solvent Fastness: Scale 1- 5	1~Poor & 5 ~ Excellent

Application

Sheetfed	•
Heatset	•
Coil Coating	o
Engineering Polymers	•
Rubber / Fiber	•
Textile Printing	•
•	Suitable
o	Limited Suitability

Note: The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



CIN No: U24220GJ1998PTC033736

NAVAPD PIGMENTS PVT. LTD.

A Govt. Of India Recognized Star Export House

 Regd. Office & Factory: 1196/1/A & B, Ghumasan Patia Road,
 Chhatral - Mehsana Highway, Rajpur - 382715, Gujarat, India

T: +91-982-503-1388 / +91-2764-278338

E: exports@navpadpigments.com W: www.navpadpigments.com